

# BCY, Inc.

697 Middle St., Middletown, CT 06457 USA

Phone: 860-632-7115

Fax: 860-632-5775

E-mail: [bcyray@msn.com](mailto:bcyray@msn.com)


Web site: [www.bcyfibers.com](http://www.bcyfibers.com)

## FAX

Date: 3/20/12  
 To: ROBERT L PIAN  
 Attn:  
 From: RAY BROWNE.

\*\*\*\*\*

TEST REPORT ON OUR ARCHERY  
 BACKSTOP NETTING FOLLOWS.  
 IT'S A FEW YEARS OLD BUT NOTHING  
 HAS CHANGED.




---



697 Middle Street, Middletown, CT 06457, U.S.A.  
 Phone: 860-632-7115 • Fax: 860-632-5775  
 e-mail: bcyray@msn.com • web site: www.bcyfibers.com

ARCHERY BACKSTOP NETTING

Date:	11/2/2007	
Style:	RPY13ANWH	Test Method
Content:	100% Polyester	ASTM D629
Weight (oz./sq.yd.):	13.75 +/- 15%	ASTM D3776
Wales (Holes)/inch:	9.75 +/- 1.75	ASTM D3887
Courses (Holes)/inch:	11.75 +/- 2.00	ASTM D3887
Instron Ball Burst (psi):	Minimum 500 Lbs.	ASTM D3787
Mullen Burst (psi):	#N/A.	ASTM D3786
Thickness:	.0475 +/- .0075	ASTM D1777
Comments:	UV Treated	

Three lots were tested for fire retardancy to meet specs for NFPA 701. The requirement for the burn length is 10". This means that the flame has to extinguish before it burns that distance. The RPY13ANWH that was tested averaged 2.5" to 3" maximum.